


# ACCURATE

FICHA TÉCNICA

## FOLDING REVERSO MADERA (GC2)

### 1 ▲ Estructura del cartón / *structure du carton*



### 2 ▲ Especificaciones técnicas

GRAMAJE <i>GRAMMAGE / GRAMMAGE</i>	ESPESOR <i>THICKNESS / ÉPAISSEUR</i>	RIGIDEZ TABER <i>STIFFNESS / RIGIDITÉ</i>	
		CD	MD
<b>g/m ±2%</b>	<b>µm ( ±5%)</b>	<b>(±15%)</b>	
265	440	14.3	28.5
275	460	15.8	32.0
290	490	18.6	37.0
305	520	21.4	41.6
325	560	25.2	49.0
350	615	31.5	60.0
375	670	39.0	73.0
400	725	46.7	88.2

### 3 ▲ Aplicaciones



### 4 ▲ Propiedades

<b>BLANCURA DE LA CARA ESTUCADA %</b> <i>BRIGHTNESS TOP % / BLANCHURE RECTO %</i>	90	ISO 2470-2
<b>CERTIFICACIONES</b> <i>CERTIFICATIONS / CERTIFICATIONS</i>	FSC, PEFC	
<b>BRILLO 75 %</b> <i>GLOSS / BRILLANCE</i>	>45	ISO 8254
<b>LISURA</b> <i>ROUGHNESS / LISSAGE</i>	≤1,4	ISO 8791-4