


ALASKA WHITE (ARTIKA)

FICHA TÉCNICA

FOLDING REVERSO BLANCO (GC1)

1 ▲ Estructura del cartón / *structure du carton*



2 ▲ Especificaciones técnicas

GRAMAJE <i>GRAMMAGE / GRAMMAGE</i>	ESPESOR <i>THICKNESS / ÉPAISSEUR</i>	RIGIDEZ TABER <i>STIFFNESS / RIGIDITÉ</i>	
		(±15%)	
g/m ±4%	µm (±4%)	CD	MD
200	282	3.3	11.8
215	308	4.3	15.7
230	336	5.3	19.1
250	378	7.0	26.1
275	428	9.7	35.7
300	474	12.1	46.1
325	520	15.2	58.3
350	568	19.3	76.6

3 ▲ Aplicaciones



4 ▲ Propiedades

BLANCURA DE LA CARA ESTUCADA % <i>BRIGHTNESS TOP % / BLANCHURE RECTO %</i>	92	ISO 2470-2
BLANCURA DEL REVERSO <i>BRIGHTNESS BOTTOM % / BLANCHURE VERSO %</i>	91	ISO 2470-2
BRILLO 75 % <i>GLOSS / BRILLANCE</i>	>45	ISO 8254-1
LISURA <i>ROUGHNESS / LISSAGE</i>	≤1,3	ISO 8791-4
CERTIFICACIONES <i>CERTIFICATIONS / CERTIFICATIONS</i>	ISO 9001, ISO 14001, ISO 50001, FSC, PEFC, ISO 45001	
TEST ROBINSON	GARANTIZADO POR UN AÑO	