


# KLAFOLD

FICHA TÉCNICA

## FOLDING REVERSO KRAFT


### 1 ▲ Estructura del cartón / *structure du carton*


**Doble capa de estucado**
*Double pigment coating / Double couche*
**Pasta química blanqueada**
*Bleached chemical pulp / pâte chimique blanchie*
**Pasta termo mecánica**
*BCTMP*
**Pasta química blanqueada**
*Bleached chemical pulp / pâte chimique blanchie*


### 2 ▲ Especificaciones técnicas

<b>GRAMAJE</b> <i>GRAMMAGE / GRAMMAGE</i>	<b>ESPESOR</b> <i>THICKNESS / ÉPAISSEUR</i>	<b>RIGIDEZ TABER</b> <i>STIFFNESS / RIGIDITÉ</i>	
<b>g/m ±5%</b>	<b>µm ( ±5%)</b>	<b>(±15%)</b>	
		CD	MD
205	252	2.5	6.0
227	288	3.4	9.0
233	320	4.7	11.1
250	375	6.4	14.6
276	393	8.4	18.8
285	455	12.7	28.7
312	515	17.4	39.9
332	555	20.4	48.3
360	600	25.1	50.7

### 3 ▲ Aplicaciones


**Alimentos secos**

**Congelados**

**Pack bebidas**

**Displays**

**Para contracolar**

### 4 ▲ Propiedades

<b>GRADO DE HUMEDAD</b> <i>MOISTURE / HUMIDITÉ</i>	5.5 - 9.5	ON-LINE
<b>ABSORCION DE AGUA</b> <i>COBB TEST / HUMIDITÉ</i>	<42	TAPPI T 441
<b>LISURA BENDTSEN</b> <i>ROUGHNESS BENDTSEN / LISSE BENDTSEN</i>	≤3	8791-4