


Performa Cream™

FICHA TÉCNICA

FOLDING REVERSO MADERA (GC2)

1 ▲ Estructura del cartón / *structure du carton*



2 ▲ Especificaciones técnicas

GRAMAJE <i>GRAMMAGE / GRAMMAGE</i>	ESPESOR <i>THICKNESS / ÉPAISSEUR</i>	RIGIDEZ TABER <i>STIFFNESS / RIGIDITÉ</i>	
		CD	MD
g/m ±4%	µm (±5%)	(±15%)	
200	310	3.5	8.3
220	340	4.5	10.8
230	360	5.4	12.8
245	405	6.8	15.5
260	440	8.2	18.6
290	500	11.1	24.6
315	560	14.5	32.4
340	610	18.1	39.8
360	650	20.3	44.9

3 ▲ Aplicaciones



4 ▲ Propiedades

BLANCURA DE LA CARA ESTUCADA % <i>BRIGHTNESS TOP % / BLANCHURE RECTO %</i>	90	ISO 2470-1
BRILLO 75 % <i>GLOSS / BRILLANCE</i>	45	ISO 8254-1
LISURA <i>ROUGHNESS / LISSAGE</i>	≤1	ISO 8791-4
TEST ROBINSON	GARANTIZADO POR UN AÑO	